

Landlok® 300

Landlok 300® turf reinforcement mat (TRM) is a three-dimensional, woven polypropylene geotextile produced by Propex Inc., and will meet the following Minimum Average Roll Values (MARV) when tested in accordance with the methods listed below. **Landlok 300®** is available in green and is specially designed for erosion control applications on steep slopes and vegetated waterways. The matrix is composed of polypropylene monofilament yarns featuring **X3® technology** woven into a uniform configuration of resilient pyramid-like projections. The material exhibits very high interlock and reinforcement capacity with both soil and root systems, demonstrates superior UV resistance, and enhances seedling emergence.

Landlok 300® conforms to the property values listed below¹ and is manufactured at a Propex facility having achieved ISO 9001:2000 certification. Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute - Laboratory Accreditation Program (GAI-LAP).

PROPERTY		TEST METHOD	MARV ² METRIC
PHYSICAL			
Mass/Unit Area		ASTM D-6566	254 g/m ²
Thickness		ASTM D-6525	6.35 mm
Light Penetration (% Passing)		ASTM D-6567	50%
Colour		Visual	Green
MECHANICAL			
Tensile Strength (Grab)		ASTM D-6818	29.2 x 26.2 kN/m
Elongation		ASTM D-6818	50% (max)
Resiliency		ASTM D-6524	70%
Flexibility		ASTM D-6575	225000 mg-cm (avg)
ENDURANCE			
UV Resistance @ 3000 hours		AMST D-4355	90%
PERFORMANCE			
Velocity ³ (vegetated)		Large Scale	6.1 m/sec
Shear Stress ³ (vegetated)		Large Scale	775 kPa
Manning's "n" ⁴ (unvegetated)		Calculated	0.030
Seedling Emergency ⁴		ECTC Draft Method #4	-
ROLL SIZES			2.6m x 32.3m

NOTES

1. The property values listed are effective 08/2006 and are subject to change without notice.
2. MARV indicated the minimum average roll value calculated as the typical minus two standards deviations. Statistically, it yields a 97.9% degree of confidence that any sample taken during quality assurance testing will exceed the value reported.
3. Maximum permissible velocity and shear stress has been obtained through vegetated testing programs featuring specific soil types, vegetation classes, flow conditions, and failure criteria. These conditions may not be relevant to every project nor are they replicated by other manufacturers. Please contact Geosynthetics for further information.
4. Calculated as typical values from large-scale flexible channel lining test programs with a flow depth of 150 - 300mm.

This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own experimentation. It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge becomes available. Since we cannot anticipate all variations in actual end use conditions, Geosynthetics Limited makes no warranties and assumes no liabilities in connection with this information. Nothing in this publication is to be considered as a licence to operate under or a recommendation to infringe any patent right.

