

Pyramat[®]

Pyramat high performance turf reinforcement mat (HPTRM) is a three-dimensional, woven polypropylene geotextile that is available in green which is specially designed for erosion control applications on steep slopes and vegetated waterways. The matrix is composed of polypropylene monofilament yarns featuring **X3[®] technology** woven into a uniform configuration of resilient pyramid-like projections. The material exhibits very high interlock and reinforcement capacity with both soil and root systems, demonstrates superior UV resistance, and enhances seedling emergence.

Pyramat conforms to the property values listed below¹ and is manufactured at a Propex facility having achieved ISO 9001:2000 certification. Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute - Laboratory Accreditation Program (GAI-LAP).

		MARV ²
PROPERTY	TEST METHOD	METRIC
PHYSICAL		
Mass/Unit Area	ASTM D-6566	455 g/m ²
Thickness	ASTM D-6525	10.2 mm
Light Penetration (% Passing)	ASTM D-6567	10%
Colour	Visual	Green
MECHANICAL		
Tensile Strength (Grab)	ASTM D-6818	58.4 x 43.8 kN/m
Elongation	ASTM D-6818	65% (max)
Resiliency	ASTM D-6524	80%
Flexibility	ASTM D-6575	615000 mg-cm (avg)
ENDURANCE		
UV Resistance @ 3000 hours	AMST D-4355	90%
PERFORMANCE		
Velocity ³ (vegetated)	Large Scale	7.6 m/sec
Shear Stress ³ (vegetated)	Large Scale	718 kPa
Manning's "n" ⁴ (unvegetated)	Calculated	0.028
Seedling Emergency ⁴	ECTC Draft Method #4	296%
ROLL SIZES		2.6 m x 27.4 m

NOTES

1. The property values listed are effective 08/2006 and are subject to change without notice.
2. MARV indicated the minimum average roll value calculated as the typical minus two standards deviations. Statistically, it yields a 97,9% degree of confidence that any sample taken during quality assurance testing will exceed the value reported.
3. Maximum permissible velocity and shear stress has been obtained through vegetated testing programs featuring specific soil types, vegetation classes, flow conditions, and failure criteria. These conditions may not be relevant to every project nor are they replicated by other manufacturers. Please contact Geosynthetics for further information.
4. Calculated as typical values from large-scale flexible channel lining test programs with a flow depth of 150 - 300mm.

This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own experimentation. It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge becomes available. Since we cannot anticipate all variations in actual end use conditions, Geosynthetics Limited makes no warranties and assumes no liabilities in connection with this information. Nothing in this publication is to be considered as a licence to operate under or a recommendation to infringe any patent right.

